



[12] Patent

<p>[11] Patent No.: GC 0000313</p> <p>[45] Date of Publishing the Grant of the Patent: 01/11/2006 6/2006</p>	<p>Number of the Decision to Grant the Patent: 5/1517</p> <p>Date of the Decision to Grant the Patent: 12/12/2005</p>
<p>[21] Application No.: GCC/P/2001/1746</p> <p>[22] Filing Date: 25/11/2001</p> <p>[30] Priority:</p> <p>[31] Priority No. [32] Priority date [33] State 09/724,072 28/11/2000 US</p> <p>[72] Inventors: 1- Russell Craig Ackerman, 2- Josiane Marie-Rose Ginestra, 3- Christian Gabriel Michel</p> <p>[73] Owner: Shell Internationale Research Maatschappij B. V., Carel van Bylandtlaan 30, 2596 HR The Hague, The Netherlands</p> <p>[74] Agent: Suleiman Ibrahim Al-Ammar</p>	<p>[51] Int. Cl.⁷: B01J 21/04, 351/10</p> <p>[56] Cited Documents:</p> <ul style="list-style-type: none"> - WO 0232570 A (SHELL OIL CO) 25 April 2002 - WO 0145839 A (GRACE W R & CO) 28 June 2001 - US 6015 485 A (CARRUTHERS JAMES DONALD et al.) 18 January 2000 - US 5002 919 A (YAMAZAKI HATSUTARO et al.) 26 March 1991 - EP 0568 913 A (DALIAN CHEMICAL PHYSICS INST) 10 November 1993 - US 4422 960 A (SHIROTO YOSHIMI et al.) 27 December 1983 - US 4555 394 A (ASAOKA SACHRO et al.) 10 September 1996 - US 4562 059 A (ASAOKA SACHRO et al.) 31 December 1985

[54] ALUMINA HAVING NOVEL PORE STRUCTURE, METHOD OF MAKING AND CATALYSTS MADE THEREFROM

[57] Abstract: Alumina having a novel pore structure characterized by the absence of macropores, no more than 5% of the total pore volume in pores greater than 350 Å, a high pore volume (greater than 0.8 cc/g measured by mercury 5 intrusion) and a bi-modal pore volume distribution character, where the two modes are separated by 10 to 200 Å and the primary pore mode is larger than the median pore diameter (MPD), calculated either by volume or by surface area, the MPD by volume being itself larger than 10 the MPD by surface area. Also provided is a method of making such alumina, and catalysts made therefrom.

No. of claims: 36

No. of figures: 9

